







P-IMP-MKT-141 · 0124 EN


mmmmm





Indo


(**tes**stone



Sizes

- Widhts: 70, 80 and 90 cm
- Lenghts from 100 to 200 cm
- Nominal thickness 3 cm

Dimensional tolerance of ±5 mm.



Product characteristics

- Completely flat on the underside
- Impact resistant
- Anti-slip Class 2 (UNE-41901)
- Anti-bacterial, preventing the proliferation of germs
- Totally waterproof
- Repairable

Finishes



Optional metalic finishes




Included

- Extra-flat shower tray
- Adjustable linear drain
- Stainless steel drain cover
- Installation manual
- Cardboard packaging

Sizes and nominal weights approx (in kg)

B A	70	80	90
100	34	38	43
110	36	41	46
120	41	46	52
130	43	49	55
140	47	54	60
150	50	56	63
160	54	61	69
170	56	64	72
180	61	69	77
190	63	71	80
200	67	76	86

Drain included



Drain cover (plate colour finish)

Customization



to cm







Special cut


ut Aı C

Anti-slip Class 3

Customer service export@b10bath.com www.b10bath.com



Indo (tesstone




Dimensions in mm

Description of materials



Tesstone from bIO is a highly durable and resistant sustainable material made of natural mineral fillers and recycled recyclates from proximity composted with PET resins (24% recycled). The bIO Tesstone shower trays benefit from a double process of surface protection and finishing with ISO NPG gelcoat and PU cover, which gives them greater impermeability, inalterability over time, resistance, ease of maintenance and one of the most matte and natural finishes on the market.



Installation options







Installation characteristics

- Installation recessed, above ground or raised
- Recommended adhesive type R-2-T (UNE-12004)
- Watertight seal with non-acetic silicone

Drops in sewage pipes should be at least 2%



Indo (tesstone

Other properties

Declared benefits:

Characteristics essential	Submissions	Harmonised technical specifications	
Cleanability	Class 1	EN 14527:2016 + A1:2019	
Durability	Class 1	EN 14527:2016 + A1:2019	
Water Evacuation	Correct	EN 14527:2016	
Stability in the background	Correct	EN 14527:2016 + A1:2019	
Resistance to chemicals and dyes	Correct	EN 14527:2016 + A1:2019	
Resistance to temperature variations	Correct	EN 14527:2016	
Slip resistance	Class 2	UNE 41901	

Resistance to chemicals:

Tested product			Exposure time	Degradation		
Bleach			24h	5		
Salfuman			24h	5		
Mr. Clean			24h	5		
Viakal			24h	4		
Vinegar			24h	4		
Ammonia			24h	5		
KH-7			24h	5		
Cillit Bang			24h	5		
Acetone			1min	4		
Isopropanol			5min	5		
Nail polish			24h	4		
Medium colour hair dye			1h	4		
Dark colour hair dye			30min	5		
Lipstick			24h	5		
Oxygenated water			24h	5		
Betadine			24h	5		
Valuation	1	Surface degradation and/or blistering				
	2	Significant change in brightness and/or colour				
	3	Moderate change in brightness and/or colour				
	4	Slight change in brightness or colour, only visible from certain inspection angles				
	5	No visible change				

The data and characteristics indicated do not bind BAÑOS 10 S.L., which reserves the right to make any changes it deems appropriate, without being bound by it uppon prior notice or replacement. Valid data except error or omission.



Ctra. Onda - Vila-real, Km. 12,6 12200 Onda (Castellón) Spain +34 964 626 300

Customer service export@b10bath.com www.b10bath.com